

KYDEX® V103 High impact fire-rated sheet

Introduction

KYDEX® V103 sheet is a recycled grade of a proprietary thermoplastic sheet that is cost competitive with other grades of thermoplastic sheet while offering improved performance.

General Information

KYDEX® V103 is Underwriters Laboratories, Inc® recognized Std 94 V-0, 5V. It has thermoforming cycle times equivalent to FR-ABS.

Suggested Applications

- Equipment Housings
- Exhibits and Displays
- Miscellaneous Applications

Features

- Formulated to substitute for FR-ABS
- Very good impact resistance
- Easy to form with excellent part definition and deep-draw characteristics
- Recognized by Underwriters Laboratories, Inc® for Std 94 V-0, 5V
- Similar forming times to FR-ABS
- Available in 7 distinctive textures

Environmental and Safety Considerations

KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.kydex.com>. For Material Safety Data Sheets, please call 800.325.3133.

KYDEX, LLC

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@kydex.com

Technical Service

Phone: 800.682.8758 ext. 581
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997 ext. 581

www.kydex.com



KYDEX® V103 High impact fire-rated sheet

Physical Properties

Property	Test Method	Typical Value ¹	
Specific Gravity	ASTM D-792	1.35	
Tensile Strength	ASTM D-638	41 MPa	6,000 psi
Flexural Strength	ASTM D-790	65.5 MPa	9,300 psi
Modulus of Elasticity	ASTM D-790	2,480 MPa	360,000 psi
Notched Izod Impact Resistance, @ 23°C (73°F)	ASTM D-256	427 J/m	8 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	94	
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	73.9°C	165°F
Flammability: Underwriters Laboratories, Inc. [®] Component Recognition	UL Standard 94 ²	V-0, 5V ³	
Mold Shrinkage % (male mold)		0.40 - 0.60	
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. ² Underwriters Laboratories, Inc., File E115252 ³ All thicknesses 0.71mm (0.028") and above Not intended for specification purposes.			

KYDEX, LLC
ISO 9001 and 14001 Certified

Customer Service
6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@kydex.com

Technical Service
Phone: 800.682.8758 ext. 581
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997 ext. 581

www.kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.